

TECHNISCHE INFORMATION

bitotex Lifestyle - LUNA



NACH EN 1307

constructie	<i>construction</i>	ISO 2424	5/64" super soft saxony
poolmateriaal	<i>yarn content</i>	ISO 2424	100% PA 6
rug	<i>backing</i>	ISO 2424	SBR free Starback
gebruiksklasse	<i>suitability</i>	EN 1307	23 / 32 general contract use
poolgewicht	<i>pile weight</i>	ISO 2424	1.650 g/m ²
totaal gewicht	<i>total weight</i>	ISO 8543	2.410 g/m ²
pooldikte	<i>pile height</i>	ISO 1766	8.0 mm
totaal dikte	<i>total thickness</i>	ISO 1765	10.0 mm
noppental	<i>tuft density</i>	ISO 1763	228,500 tufts/m ²
breedte	<i>width</i>	CEN/TS 14159	ca. 4 m
warmtedoorlaatweerstand	<i>thermal resistance</i>	ISO 8302	0.15 m ² K/W
brandklasse	<i>flammability</i>	ISO 13501-1	Cfl-S1
contactgeluidsisolatie	<i>impact sound insulation</i>	ISO 140-8/717-2	25 dB
structure	<i>Konstruktion</i>	ISO 2424	5/64" super soft saxony
composition	<i>Polmateriaal</i>	ISO 2424	100% PA 6
dossier	<i>Beschichtung</i>	ISO 2424	SBR free Starback
classement d'usage	<i>Zusatzeignung</i>	EN 1307	23 / 32 general contract use
poids de velours	<i>Poleinsatzgewicht</i>	ISO 2424	1.650 g/m ²
poids total	<i>Gesamtgewicht</i>	ISO 8543	2.410 g/m ²
hauteur du velours	<i>Polschichtdicke</i>	ISO 1766	8.0 mm
épaisseur totale	<i>Gesamtdicke</i>	ISO 1765	10.0 mm
densité	<i>Noppenzahl</i>	ISO 1763	228,500 tufts/m ²
dimensions	<i>Breite</i>	CEN/TS 14159	ca. 4 m
résistance thermique	<i>Wärmedurchlasswiderstand</i>	ISO 8302	0.15 m ² K/W
comportement au feu	<i>Brandverhalten</i>	ISO 13501-1	Cfl-S1
isolation acoustique	<i>Trittschallverbesserungsmaß</i>	ISO 140-8/717-2	25 dB

FARBEN

102 Milky Way	142 Mars	261 Neptune
119 Stardust	149 Earth	285 Red Dwarf
129 Venus	181 Cosmos	
131 Jupiter	189 Pluto	
135 Galaxy	253 Mercury	

PRODIS RATING AND INFORMATION



KONTAKT

bito Aktiengesellschaft
 Bielefelder Straße 6
 10709 Berlin
 030. 477 998 0
 info@bito-ag.de
 www.bitto-ag.de



Alle technische specificaties zijn onderhevig aan productietoleranties. Voor alle voorwaarden en onderhoudsadvies verwijzen wij u graag naar onze website.

All specifications are subject to normal manufacturing tolerances. For all Terms & Conditions, care and maintenance, please visit our website.

Toutes les spécifications techniques sont sujet aux tolérances de fabrication. Merci de consulter notre website pour toutes informations et les conseils d'entretien.

Alle technische Daten unterliegen Produktionstoleranzen. Bedingungen und Pflegeempfehlungen finden Sie auf unserer Website.