

## TECHNISCHE INFORMATION

## bitotex Lifestyle - PALMARES


### NACH EN 1307

constructie	<i>construction</i>	ISO 2424	1/10" soft cut pile
poolmateriaal	<i>yarn content</i>	ISO 2424	polyamide PA 6
rug	<i>backing</i>	ISO 2424	Sbr free Starback
gebruiksklasse	<i>suitability</i>	EN 1307	23/32 general contract use
poolgewicht	<i>pile weight</i>	ISO 2424	1.500 g/m <sup>2</sup>
totaal gewicht	<i>total weight</i>	ISO 8543	2.400 g/m <sup>2</sup>
pooldikte	<i>pile height</i>	ISO 1766	7.4 mm
totaal dikte	<i>total thickness</i>	ISO 1765	10.2 mm
noppental	<i>tuft density</i>	ISO 1763	252.000 tufts/m <sup>2</sup>
breedte	<i>width</i>	CEN/TS 14159	ca 4 and 5 m
rapport	<i>pattern repeat</i>	CEN/TS 14159	0 mm
warmteoorlaatweerstand	<i>thermal resistance</i>	ISO 8302	0.15 m <sup>2</sup> K/W
brandklasse	<i>flammability</i>	ISO 13501-1	Cfl-s1
contactgeluidsisolatie	<i>impact sound insulation</i>	ISO 140-8/717-2	25dB
structure	<i>Konstruktion</i>	ISO 2424	1/10" soft cut pile
composition	<i>Polmaterial</i>	ISO 2424	polyamide PA 6
dossier	<i>Beschichtung</i>	ISO 2424	Sbr free Starback
classement d'usage	<i>Zusatzeignung</i>	EN 1307	23/32 general contract use
poids de velours	<i>Poleinsatzgewicht</i>	ISO 2424	1.500 g/m <sup>2</sup>
poids total	<i>Gesamtgewicht</i>	ISO 8543	2.400 g/m <sup>2</sup>
hauteur du velours	<i>Polschichtdicke</i>	ISO 1766	7.4 mm
épaisseur totale	<i>Gesamtdicke</i>	ISO 1765	10.2 mm
densité	<i>Noppenzahl</i>	ISO 1763	252.000 tufts/m <sup>2</sup>
dimensions	<i>Breite</i>	CEN/TS 14159	ca 4 and 5 m
raccord	<i>Rapport</i>	CEN/TS 14159	0 mm
résistance thermique	<i>Wärmedurchlasswiderstand</i>	ISO 8302	0.15 m <sup>2</sup> K/W
comportement au feu	<i>Brandverhalten</i>	ISO 13501-1	Cfl-s1
isolation acoustique	<i>Trittschallverbesserungsmaß</i>	ISO 140-8/717-2	25dB

### FARBEN

102 Snow	141 Fountain	234 Olive
122 Dust	149 Pumice	235 Coral
129 Silver	169 Concrete	243 Terra cotta
133 Taupe	188 Heather	253 Gold
136 Easy	189 Kohl	281 Ink

### PRODIS RATING AND INFORMATION



EN 14041

EN 1307



PRODIS: 970AE343

DOP: 1025-126443

### KONTAKT

bito Aktiengesellschaft  
Bielefelder Straße 6  
10709 Berlin  
030. 477 998 0  
info@bito-ag.de  
www.bit-ag.de



Alle technische specificaties zijn onderhevig aan productietoleranties. Voor alle voorwaarden en onderhoudsadvies verwijzen wij u graag naar onze website.

All specifications are subject to normal manufacturing tolerances. For all Terms & Conditions, care and maintenance, please visit our website.

Toutes les spécifications techniques sont sujet aux tolérances de fabrication. Merci de consulter notre website pour toutes informations et les conseils d'entretien.

Alle technische Daten unterliegen Produktionstoleranzen. Bedingungen und Pflegeempfehlungen finden Sie auf unserer Website.

v3