

TECHNISCHE INFORMATION

bitotex Lifestyle - VICTORY


NACH EN 1307

constructie	<i>construction</i>	ISO 2424	1/10" soft cut pile
poolmateriaal	<i>yarn content</i>	ISO 2424	polyamide PA 6
rug	<i>backing</i>	ISO 2424	sbr free Starback
gebruiksklasse	<i>suitability</i>	EN 1307	23/32 general contract use
poolgewicht	<i>pile weight</i>	ISO 2424	900 g/m ²
totaal gewicht	<i>total weight</i>	ISO 8543	2.000 g/m ²
pooldikte	<i>pile height</i>	ISO 1766	3.8 mm
totaal dikte	<i>total thickness</i>	ISO 1765	6.5 mm
noppental	<i>tuft density</i>	ISO 1763	204.000 tufts/m ²
breedte	<i>width</i>	CEN/TS 14159	ca 4 and 5 m
rapport	<i>pattern repeat</i>	CEN/TS 14159	0 mm
warmte doorlaat weerstand	<i>thermal resistance</i>	ISO 8302	0.12 m ² K/W
brandklasse	<i>flammability</i>	ISO 13501-1	Cfl-s1
contactgeluidsisolatie	<i>impact sound insulation</i>	ISO 140-8/717-2	25dB
structure	<i>Konstruktion</i>	ISO 2424	1/10" soft cut pile
composition	<i>Polmaterial</i>	ISO 2424	polyamide PA 6
dossier	<i>Beschichtung</i>	ISO 2424	sbr free Starback
classement d'usage	<i>Zusatzeignung</i>	EN 1307	23/32 general contract use
poids de velours	<i>Poleinsatzgewicht</i>	ISO 2424	900 g/m ²
poids total	<i>Gesamtgewicht</i>	ISO 8543	2.000 g/m ²
hauteur du velours	<i>Polschichtdicke</i>	ISO 1766	3.8 mm
épaisseur totale	<i>Gesamtdicke</i>	ISO 1765	6.5 mm
densité	<i>Noppenzahl</i>	ISO 1763	204.000 tufts/m ²
dimensions	<i>Breite</i>	CEN/TS 14159	ca 4 and 5 m
raccord	<i>Rapport</i>	CEN/TS 14159	0 mm
résistance thermique	<i>Wärmedurchlasswiderstand</i>	ISO 8302	0.12 m ² K/W
comportement au feu	<i>Brandverhalten</i>	ISO 13501-1	Cfl-s1
isolation acoustique	<i>Trittschallverbesserungsmaß</i>	ISO 140-8/717-2	25dB

FARBEN

102 Frost	124 Brightness	136 Zephyr	178 Perseverance
112 Sand	125 Innocence	151 Modesty	189 Carbon
113 Happiness	129 Silver	155 Passion	253 Caramel
121 Satisfaction	133 Taupe	168 Lavender	264 Lagoon
122 Slow	135 Triumph	169 Mouse	

PRODIS RATING AND INFORMATION



PRODIS: E8D79CBB
DOP: 1025-127364

KONTAKT

bito Aktiengesellschaft
Bielefelder Straße 6
10709 Berlin
030. 477 998 0
info@bito-ag.de
www.bitto-ag.de



Alle technische specificaties zijn onderhevig aan productietoleranties. Voor alle voorwaarden en onderhoudsadvies verwijzen wij u graag naar onze website.

All specifications are subject to normal manufacturing tolerances. For all Terms & Conditions, care and maintenance, please visit our website.

Toutes les spécifications techniques sont sujet aux tolérances de fabrication. Merci de consulter notre website pour toutes informations et les conseils d'entretien.

Alle technische Daten unterliegen Produktionstoleranzen. Bedingungen und Pflegeempfehlungen finden Sie auf unserer Website.